REPORT DOCUMENTATION PAGE

AD-A203 168	**1b. RESTRICTIVE MARKINGS**
2b. DECLASSIFICATION / DOWNGRADING SCHEDULE JAN 2 6 1989	**3. DISTRIBUTION / AVAILABILITY OF REPORT** Approved for public release; distribution unlimited.
4. PERFORMING ORGANIZATION REPORT NUMBER(S)	**5. MONITORING ORGANIZATION REPORT NUMBER(S)** ARO 21623.26-PH

6a. NAME OF PERFORMING ORGANIZATION	6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION
Research Foundation of SUNY-Albany		U. S. Army Research Office

6c. ADDRESS (City, State, and ZIP Code)	7b. ADDRESS (City, State, and ZIP Code)
P.O. Box 9 Albany, NY 12201	P. O. Box 12211 Research Triangle Park, NC 27709-2211

8a. NAME OF FUNDING / SPONSORING ORGANIZATION	8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER
U. S. Army Research Office		DAAG-29-85-K-0097

8c. ADDRESS (City, State, and ZIP Code)	10. SOURCE OF FUNDING NUMBERS			
P. O. Box 12211 Research Triangle Park, NC 27709-2211	PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO.	WORK UNIT ACCESSION NO.

11. TITLE (Include Security Classification)
Theoretical Studies of the Chemistry and Physics of Oxygen in Silicon

12. PERSONAL AUTHOR(S)
Lawrence C. Snyder and James W. Corbett

13a. TYPE OF REPORT	13b. TIME COVERED	14. DATE OF REPORT (Year, Month, Day)	15. PAGE COUNT
Final	FROM 4/15/85 TO 4/14/88	11/18/88	9

16. SUPPLEMENTARY NOTATION
The view, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)
FIELD	GROUP	SUB-GROUP	Semiconductor Theory, Silicon Defects, Oxygen Thermal Donors.

19. ABSTRACT (Continue on reverse if necessary and identify by block number)

We have developed a cyclic-cluster program to compute the structure and properties of defects in crystalline solids. We have found the semi-empirical electronic structure method MINDO/3 to give the best account of the structure, stability and states near the gap for defects in silicon. We have applied the cyclic cluster program to describe the chemistry and physics of hydrogen and oxygen in a silicon crystal. We have concluded that a di-ylid is a promising candidate for the core of the 450° oxygen thermal donor in silicon. We have discovered that a four-member ring containing two oxygen atoms is likely to diffuse much faster than interstitial oxygen in silicon. We have applied pertubation theory to give a qualitative explanation of the ladder of effective mass states associated with oxygen clusters in silicon and germanium.

20. DISTRIBUTION / AVAILABILITY OF ABSTRACT	21. ABSTRACT SECURITY CLASSIFICATION
☐ UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT. ☐ DTIC USERS	Unclassified
22a. NAME OF RESPONSIBLE INDIVIDUAL	**22b. TELEPHONE (Include Area Code)** **22c. OFFICE SYMBOL**

DD FORM 1473, 84 MAR   83 APR edition may be used until exhausted.   SECURITY CLASSIFICATION OF THIS PAGE
All other editions are obsolete.   UNCLASSIFIED

89 1 17 282

THEORETICAL STUDIES OF THE CHEMISTRY AND PHYSICS
OF OXYGEN IN SILICON

FINAL REPORT

LAWRENCE C. SNYDER AND JAMES W. CORBETT

NOVEMBER 18, 1988

U. S. ARMY RESEARCH OFFICE

CONTRACT NO. DAAG29-85-K-0097

RESEARCH FOUNDATION OF
THE STATE UNIVERSITY OF NEW YORK

APPROVED FOR PUBLIC RELEASE;
DISTRIBUTION UNLIMITED.

THEORETICAL STUDIES OF THE CHEMISTRY AND PHYSICS OF OXYGEN IN SILICON

THE PROBLEM STUDIED

Broadly stated, we have attempted to describe the chemistry and physics of oxygen in a silicon crystal. To do this we have combined the semi-empirical electronic structure methods developed by chemists with the cyclic cluster methods developed by physicists. Our tools are of general applicability, and may be used with previously developed parameters to describe various defect structures in silicon containing oxygen, hydrogen, and other elements.

Our interest has centered on elucidating the nature of the core of the thermal donors which are formed when crystalline silicon containing dispersed interstitial oxygen is annealed at 450°C. A series of thermal donors appears to be formed by the sequential addition of oxygen atoms. They have been studied using infrared (IR) spectroscopy, electron spin resonance (ESR), and electron-nuclear double resonance (ENDOR). These tools show that the thermal donors are shallow double donors with a pair of electrons in effective-mass states. The kinetics for thermal donor formation have often been interpreted to require an enhanced diffusion rate for interstitial oxygen or an oxygen dimer. For this reason we have studied the mechanism and energetics of diffusion of oxygen.

We are also interested in relatively well understood defects containing oxygen in silicon: these include interstitial oxygen, oxygen in a vacancy, and two oxygen atoms in a vacancy. These systems provide a test of any methods we develope.

Properties of defects of interest include structure, thermodynamic stability, location of electronic states relative to the gap, vibrational frequencies, and potential surfaces for structural changes.

Because of the increasing interest in the role of hydrogen in silicon, we have undertaken studies of the structures by which hydrogen is bound to the crystal and the diffusion path for hyrogen.

SUMMARY OF THE MOST IMPORTANT RESULTS

We have developed a cyclic-cluster program to compute the structure and properties of defects in crystalline solids [1]. We incorporated several semiemperical electronic structure methods in cyclic cluster and molecular cluster programs and found the Modified Intermediate Neglect of Differential Overlap (MINDO/3) to give the most satisfactory description of defect electronic states close to the gap in silicon [2]. We found the original MNDO method was not rotationally invariant with a resulting loss of degeneracy of energy levels of cyclic clusters. We proposed a solution to this problem [3].

Application of the cyclic cluster program to describe the bonding of hydrogen in silicon showed the most stable bonding to be at a bond centered position [4]. We have reviewed related experiments which appear to support this conclusion [5]. The potential surface for the diffusion of hydrogen in silicon was also explored in paper [6]. Cyclic cluster calculations were made to decribe the passivation by hydrogen of substitutional sulfur in silicon. This work showed the hydrogen to bond to the silicon atoms neighboring the sulfur atom [7]. Major results of our hydrogen related work are summarized in two review articles [8,9].

A copy of the MINDO/3 cylic cluster and molecular cluster programs has been given to Dr. Arthur Edwards of the Electronics Device and Technology Laboratory at Fort Monmouth.

We believe that oxygen becomes trivalent in its bonding to silicon to form the oxygen thermal donor. The silicon oxygen-ylid [10,11,12] was the first such structure proposed by us for the core of the oxygen thermal donor. A single ylid is of C_{2v} symmetry and would have an oxygen atom on the rotation axis of the defect. This disagrees with the conclusion from ENDOR spectra that although the thermal donor contains oxygen, none is on the rotation axis. For this reason we have explored a di-ylid, four-member rings, and other models for the core of the thermal donor. These calculations showed that a vacancy model favored by ENDOR spectroscopists is thermodynamically unstable [13]. We examined the location of gap states and qualitative ENDOR splittings for these models and

concluded that a di-ylid model for the thermal donor core is promising and should be studied further [14].

Our studies of various bonding structures in of oxygen in silicon lead us to the surprizing conclusion that a four-member ring containing two oxygen atoms is stable with respect to dissociation into two interstitial oxygen atoms and that the four member ring may be a fast diffusing species in silicon [15,16]. This has lead us to undertake a systematic study using the cyclic cluster method of one- and two-oxygen defects in silicon [17].

We have found a simple application of perturbation theory to be helpful in understanding the ladder of effective mass states in silicon associated with a postulated series of donor cores with an increasing number of oxygen atoms [18]. It has been used to explain a new shallow donor series in silicon [19] as well as spectra of thermal donor series in germanium [20,21,22].

We have had success in fitting the observed kinetics of formation of the thermal donor series by assuming that the smallest electrically active species contains five oxygen atoms [23]. We find our model to predict an oxygen depletion rate which is in excellent agreement with experimental findings [24,25]. Some of our findings were summarized in an invited review paper [26].

We have explored the application of the concept of fractals to ion cascades [27,28] and disordered impurities in solids [29].

We published four additional papers more distantly related to the main thrust of our research [30,31,32,33].

RESEARCH OPPORTUNITIES

We believe that molecular cluster and cyclic cluster calculations can be profitably be used to study the etching of silicon by hydrogen [34] and other species. We also intend to approach the study of the structure and electronic states of surfaces and interfaces using these tools.

We have modified our programs to compute the vibrations of subsets of atoms moving in the potental provided by the remaining atoms of the cluster. This program has given very encouraging results in describing the infrared spectra of interstitial oxygen and

other oxygen defects in silicon. We believe a large research opportunity exists here.

I have been funded by the National Research Council to join Dr. Arthur Edwards of the U. S. Army Electronics and Technology Lab. in Fort Monmouth in developing MINDO/3 parameters for gallium, arsenic, aluminum, and nitrogen for application of the methods we have developed here to new materials. That collaboration may lead to a proposal to study defects in gallium arsenide and related materials.

LIST OF PUBLICATIONS

[1]. Evaluation of Semiemperical Quantumchemical Methods in Solid State Applications. II. Cyclic Cluster Calculations on Silicon, P. Deak, L. C. Snyder, Phys. Rev. **B36**, 9619 (1987).

[2]. Evaluation of Semiemperical Quantumchemical Methods in Solid State Applications. I. Molecular Cluster Calculations on Defect in Silicon, P. Deak, L. C. Snyder, R. K. Singh and J. W. Corbett, Phys. Rev. **B36**, 9612 (1987).

[3]. A Possible Solution to the Rotational Invarience and Silicon Parameter Problem in the MNDO Approximation, P.Deak and L. C. Snyder, Int J. of Quant. Chem. Symposium 21, 547 (1987).

[4]. The State and Motion of Hydrogen in Crystalline Silicon, P. Deak, L. C. Snyder and J. W. Corbett, Phys. Rev. **B37**, 6887 (1988).

[5]. The Self-Trapping of Hydrogen in Semiconductors, P. Deak, L. C. Snyder, J. L. Lindstrom, J. W. Corbett, S. J. Pearton and A. J. Tavendale, Phys. Lett. **A126**, 427 (1988).

[6]. The Diffusion and Electronic Structure of Hydrogen in Silicon, Peter Deak, Lawrence C. Snyder and James W. Corbett, Lecture Notes in Physics, Vol. 301, New Developments in Semiconductor Physics, Edited by G. Ferenczi and F. Beleznay, Springer-Verlag, New York (1988) p 163.

[7]. Hydrogen Passivation of a Substitutional Sulfur Defect in Silicon, A. S. Yapsir, P. Deak, Raj K. Singh, L. C. Snyder, J. W. Corbett and T. M. Lu, Phys. Rev. **B38**, 0000 (1988).

[8]. Hydrogen in Crystalline Semiconductors, S. J. Pearton, J. W. Corbett and T. S. Shi, Applied Physics **A43**, 153 (1987).

[9]. Hydrogen in Semiconductors, J. W. Corbett, Symposium Vol. 104, Defects in Electronic Materials, Edited by M. Stavola, S. J. Pearton and G. Davies, Materials Research Society, Pittsburgh (1988) p 229.

[10]. MNDO Calculations on Molecular Clusters Chosen to Model the Bonding of Oxygen in Silicon, Xie Ying, L. C. Snyder, S. N. Sahu and J. W. Corbett, Phys. Stat. Sol. (b) **130** 333 (1985).

[11]. The Silicon-Oxygen Ylid: A Possible Structure for the (450°C) Oxygen Thermal Donor in Silicon, Lawrence C. Snyder and James W. Corbett, Thirteenth International Conference on Defects in Semiconductors, edited by L. C. Kimerling and J. H. Parsey Jr., (The Metallurgical Soc. of AIME, N. Y., 1985).

[12]. Cluster Computations Related to Silicon Thermal Donors, Lawrence C. Snyder and James W. Corbett, proceedings of the Symposium on Oxygen, Carbon, Hydrogen, and Nitrogen in Silicon, eds. J. C. Mikkelsen Jr., S. J. Pearton, J. W. Corbett and S. J. Pennycook, Vol. 59 (Materials Research Society, Pittsburgh, 1986) p.207.

[13]. Molecular Cluster and Cyclic Cluster Calculations on Models for the Core of the 450°C Oxygen Thermal Donor in Silicon, L. C. Snyder, P. Deak, R. Wu and J. W. Corbett, to be published in the Proceedings of the Third International Conference on Shallow Impurities in Semiconductors, Vol. 95 of the Institute of Physics Conference Series (1988).

[14]. Computation of Structure Stability and Gap States for Core Models of the Oxygen Thermal Donor in Silicon, L. C. Snyder, P. Deak, R. Wu and J. W. Corbett, to be published in the Proceedings of the Fifteenth International Conference on Defects in Semiconductors, Trans. Tech. Publications (1988).

[15]. On the Diffusion of Oxygen Dimer in a Silicon Crystal, L. C. Snyder, J. W. Corbett, P. Deak and R. Wu, Symposium Vol. 104, Defects in Electronic Materials, Edited by M. Stavola, S. J. Pearton and G. Davies, Materials Research Society, Pittsburgh (1988) p 179.

[16]. On the Diffusion of Oxygen in a Silicon Crystal, Lawrence C. Snyder, James W. Corbett, Peter Deak and Rongzhi Wu, Lecture Notes in Physics, Edited by G. Ferenczi and F. Beleznay, Springer-Verlag, New York (1988) p 147.

[17]. One- and Two-Oxygen Defects in Silicon - A Theoretical Study, P. Deak, L. C. Snyder, J. W. Corbett, R. Wu and A. Solyom, to be published in the Proceedings of the Fifteenth International Conference on Defects in Semiconductors, Trans. Tech. Publications (1988).

[18]. Perturbation Model for the Thermal Donor Energy Spectrum in Silicon, J. T. Borenstein, J. W. Corbett, M. Herder, S. N. Sahu, and L. C. Snyder, J. Phys. C. 19, 2893 (1986).

[19]. The New Shallow Donor Series in Silicon, J. A. Griffin, H. Navarro, J. Weber, L. Genzel, J. T. Borenstein, J. W. Corbett and L. C. Snyder, J. Phys. C.: 19, L579 (1986).

[20] Comments on the Thermal Donor States in Silicon and Germanium, C. S. LaPorta, J. C. Kimball, J. T. Borenstein and J. W. Corbett, J Phys. C.: 19, L627 (1986).

[21]. A Unified Treatment of the Thermal Donor Heirarchies in Silicon and Germanium, proceedings of the Symposium on Oxygen Carbon, Hydrogen and Nitrogen in Crystalline Silicon, ed by J. C. Mikkelsen Jr., S. J. Pearton J. W. Corbett and S. J. Pennycook, Vol. 59, Materials Research Society, Pittsburgh, PA (1986) p 159.

[22]. Unified Model for the Thermal Donor Energy Spectra in Silicon and Germanium, Jeffrey T. Borenstein and James w. Corbett, Physics Letters A 115, 55 (1986).

[23]. Formation Kinetics of Thermal Donors in Silicon, Jeffrey T. Borenstein, David peak, and James W. Corbett, proceedings of the Symposium on Oxygen Carbon, Hydrogen and Nitrogen in Crystalline Silicon, ed by J. C. Mikkelsen Jr., S. J. Pearton J. W. Corbett and S. J. Pennycook, Vol. 59, Materials Research Society, Pittsburgh, PA (1986) p 173.

[24]. Depletion of Interstitial Oxygen and the Thermal Donor Models, Jeffrey t. Borenstein, Vijay A. Singh and James W. Corbett, J. Appl. Phys. 62 1287 (1987).

[25]. Metastable Model for Interstitial Oxygen Depletion in Silicon, K. Banerjee, V. A. Singh and J. W. Corbett Semicond. Sci. and Tech. 3 452 (1988).

[26]. Oxygen in Silicon, James W. Corbett, Peter Deak, J. Lennart Lindstrom, Laura M. Roth and Lawrence C. Snyder, to be published in the Proceedings of the Fifteenth International Conference on Defects in Semiconductors, Trans. Tech. Publications (1988).

[27]. Fractal Dimension of Ion Cascades in Matter, G. O. Williams, T. Diaz de la Rubia, J. W. Corbett, N. Cue, W. A. Lanford and J. F. Ziegler, Radiation Effects Express, 1, 175 (1988).

[28]. Collision Cascades and Fractals, G. O. Williams, V. A. Singh and J. W. Corbett, Phys. Stat. Sol. (b) 144 K1-5 (1987).

[29]. Fractal Character of the Electronic Eigenstates of a Disordered Impurity Cluster in a Solid, Vijay A. Singh and J. W. Corbett, J. Phys. C: 21 133 (1988).

[30]. Defect Aggregates in Silicon, J. W. Corbett J. C. Corelli, U. Desnica and L. C. Snyder in Microscopic Identification of Electronic Defects in Semiconductors, eds., N. Johnson, S. Bishop, and G. D. Watkins (Materials Research Society, NY, 1985).

[31]. Paired Temperature Spectroscopy (PATS) for Gap States in Ordered and Disordered Semiconductors. I: Theoretical Analysis, Raj K. Singh, Vijay A. Singh and J. W. Corbett, Semicond. Sci. Technol. 2, 716 (1987).

[32]. Defect Centers Generated by Hydrogen Ion Implantation on Al/Si(n) Schoztky Diodes and Their Role in Changing Barrier Heights, A. S. Yapsir, P. Hadizad, T.-M. Lu, J. C. Corelli and J. W. Corbett, Phys. Rev. B37, 8982 (1988).

[33]. Iron-Vacancy-Oxygen Complex in Silicon, Z. -P. You, M. Gong, J. -Y. Chen, and J. W. Corbett, J. Appl. Phys. 63 , 324 (1988).

[34]. Etching Silicon Surfaces with Hydrogen Atoms, F. Lu, J. W. Corbett and L. C. Snyder, accepted by Phys. Lett.

PARTICIPATING SCIENTIFIC PERSONNEL

Professor Lawrence C. Snyder

Professor James W. Corbett

Dr. Peter Deak

Dr. S. N. Sahu

Dr. Vijay A. Singh

Mr. Rongzhi Wu

Mr. Michael Reed

Mr. Michael Plitkins

Miss Diana Reed

Miss Chu Haiyan

Mr. Kenneth Zinssar